



Technical Data Sheet

DOD-24607A NON-FLAMING (INTUMESCENT) ENAMEL

PRODUCT: A government specification, non-flaming enamel formulated to meet DOD-24607A.

DESCRIPTION: DOD-24607A non-flaming enamel is an intumescent, non-flaming coating that is resistant to burning and flaming.

PROPERTIES: COLORS - Per Fed-Std 595B
 FINISH - Semigloss
 SOLIDS(Weight) - 79- 82%
 PIGMENT(Weight) - 52 - 54%
 VISCOSITY - 80 - 90 KU

DRYING TIMES: TO TOUCH - 2 Hours
 DRY HARD - 5 hours

ADVANTAGES: 1. Non-Flaming (intumescent) Properties
 2. Meets DOD-24607A
 3. Resistant to Burning
 4. Air Dry-Semigloss Finish

USES: 1. Aerospace Applications
 2. Submarines
 3. Factories
 4. Industrial Facilities

APPLICATION: Apply by brush, roller or spray methods. For brush and roll, thin with Mineral Spirits Reduce at 10% by volume. For spray application, thin with Xylene at 10-15% by volume. Apply to a dry film thickness of 1.5 - 2.0 mils.

Fast. Reliable. Accurate. Superior Coatings of America

Address: P.O. Box 409 Clinton, MI 49236 Office Phone: 734-580-2089 Email: sales@superiorsalesdist.com
www.superiorsalesdist.com



Technical Data Sheet

PRECAUTIONS:

KEEP OUT OF REACH OF CHILDREN.

USE WITH ADEQUATE VENTILATION.

AVOID CONTACT WITH SKIN AND EYES.

READ MATERIAL SAFETY DATA SHEET BEFORE USING.

CONTENTS ARE FLAMMABLE.

Fast. Reliable. Accurate. Superior Coatings of America

Address: P.O. Box 409 Clinton, MI 49236 Office Phone: 734-580-2089 Email: sales@superiorsalesdist.com
www.superiorsalesdist.com