



## Technical Data Sheet

**DOD-P-15328D**  
GREEN WASH PRIMER

**PRODUCT:** A two-component metal pretreatment wash primer.

**DESCRIPTION:** Metal Pretreatment Wash Primer is a two-component, zinc-chromate pigmented, polyvinyl butyral coating. It serves as an excellent bond coat to many surfaces including aluminum, galvanized metal, lead, brass, magnesium, fiberglass and ferrous metals. May also be used on blasted clean steel surfaces with some vinyl systems. This primer is available in two transparent colors; green and yellow. Meets specifications DOD-P-15328D(green).

**PROPERTIES:**

SOLIDS(Weight) - 19 - 21%  
SOLIDS(Volume) - 15 - 17%  
VISCOSITY - 57 - 75 KU  
COLORS - Green  
POT LIFE (77 degrees F) - 8 Hours\*\*

**DRY TIME:**

TACK FREE - 15 Minutes\*\*  
DRY HARD - 30 Minutes\*\*  
  
SHELF LIFE - 1 Year  
THINNER - T-120-66  
COVERAGE - 750 - 800 sq. Ft/gal  
MIXING RATIO - 4:1 BY VOLUME

\*\* Dependent on temperature and humidity levels.

**ADVANTAGES:**

1. Promotes Excellent Base
2. Serves as a Tie-coat
3. Fast Dry
4. Excellent Coverage Rate
5. Meets Government Specifications

***Fast. Reliable. Accurate. Superior Coatings of America***

Address: P.O. Box 409 Clinton, MI 49236    Office Phone: 734-580-2089    Email: sales@superiorsalesdist.com  
www.superiorsalesdist.com



## Technical Data Sheet

---

**SURFACE PREPARATION:** *Steel, Non-Ferrous Metals & Galvanizing.*

Surface to be coated must be clean, dry, and free of all foreign contaminants including grease, oil, dirt and paint. Clean in accordance with SSPC-SP-1. Alloys that oxidize must be lightly sanded to remove all loose material. Dirt and dust are best removed with a stiff bristle brush and by compressed air. Grease and oil should be removed by cleaning with appropriate solvents such as mineral spirits, lacquer wash thinner or xylene.

**MIXING INSTRUCTIONS:** Thoroughly mix each component before combining. Add 2 parts thinner to 1 part of Acid Component. Add this mixture to 4 parts of the primer (resin component) slowly while mixing. Slight additional thinning may be done with thinner component, but not with the acid component. Do not mix more material than can be used in 8 hours.

**PRECAUTIONS:**

KEEP OUT OF REACH OF CHILDREN.

USE WITH ADEQUATE VENTILATION.

AVOID CONTACT WITH SKIN AND EYES.

READ MATERIAL SAFETY DATA SHEET BEFORE USING.

CONTENTS ARE FLAMMABLE.

***Fast. Reliable. Accurate. Superior Coatings of America***

Address: P.O. Box 409 Clinton, MI 49236    Office Phone: 734-580-2089    Email: [sales@superiorsalesdist.com](mailto:sales@superiorsalesdist.com)  
[www.superiorsalesdist.com](http://www.superiorsalesdist.com)