



Technical Data Sheet

MIL-PRF-3043C
AMS 3132
PERMANENT RESIN COATING

PRODUCT DESCRIPTION: A thermosetting resin coating for surfaces of engine components and metal parts. Dyed to a semi-transparent blue color which changes to green upon proper baking.

TYPICAL PROPERTIES:

COLOR - Blue in package, Green after bake
SOLIDS(Volume) - 13 - 14%

DRYING CYCLE: After air drying for one hour, the coated parts should be baked until the resin coating exhibits a distinct green coloration. Test procedures call for the metal panels to be baked at 325 Degrees F +/- 5 Degrees, however, the size and shape of the parts may require deviation from this schedule in order to obtain full cure and hardness.

APPLICATION AND REDUCTION: Normal application is dipping or spraying at packaged viscosity. Apply to a dry film thickness of 0.5 to 0.7 mils. If necessary, thinning may be done with MIL-T-81772B Type 3 or MIL-T-18362 not to exceed 5% by volume.

STORAGE:

STORE INDOORS AT ROOM TEMPERATURE.

KEEP AWAY FROM HEAT, SPARKS AND OPEN FLAME.

READ MSDS BEFORE USE. FOR INDUSTRIAL USE ONLY.

Fast. Reliable. Accurate. Superior Coatings of America

Address: P.O. Box 409 Clinton, MI 49236 Office Phone: 734-580-2089 Email: sales@superiorsalesdist.com
www.superiorsalesdist.com