



## MIL-PRF-81352C TY. I Acrylic Lacquer

### Technical Data Sheet (Page 1 of 2)

**Description:**

A general purpose, exterior protective acrylic lacquer coating for metal surfaces. This coating is particularly formulated for resistance to diester lubricating oil and heat for the aircraft industry. Available in gloss, semigloss and lusterless finishes.

**Physical Properties:**

<b>Colors:</b>	All 595 Colors
<b>Max VOC:</b>	340 G/L
<b>Dry Hard:</b>	40 Minutes
<b>Resistant to:</b>	Heat, Weather, Water, Hydrocarbons, Lubricating Oil

**Typical Uses:**

- (1) Steel
- (2) Machinery
- (3) Aircraft
- (4) Vehicles
- (5) Equipment
- (6) Towers

**Application Characteristics:**

- (1) Meets MIL-L-81352B Type I
- (2) Weather Resistant
- (3) Fast Dry
- (4) Full Color Range, 595 Colors
- (5) Durable Exterior Coating

**Fast. Reliable. Accurate. Superior Coatings of America**

Address: P.O. Box 409 Clinton, MI 49236    Office Phone: 734-580-2089    Email: [sales@superiorsalesdist.com](mailto:sales@superiorsalesdist.com)  
[www.superiorsalesdist.com](http://www.superiorsalesdist.com)



## **MIL-PRF-81352C TY. I Acrylic Lacquer**

### **Technical Data Sheet (Page 2 of 2)**

#### **APPLICATION & REDUCTION:**

MIL-PRF-81352C Type I Acrylic Lacquers can be applied by conventional or airless spray application. For spraying, thin up to 10% or as needed with MIL-T-81772B TY.3 Thinner. For brushing, reduce up to 10% with MIL-T-81772B TY.3 Thinner Brush small areas only.

#### **SURFACE PREPARATION:**

Surface must be clean, dry, and free of all contamination before application of primer.

#### **STEEL:**

Surface must be clean and free of all oil, grease, and foreign material. Badly rusted or pitted steel should be cleaned by commercial sandblasting and primed the same day.

#### **PRECAUTIONS:**

Contents are FLAMMABLE.

Keep away from heat and open flame.

KEEP OUT OF THE REACH OF CHILDREN.

Do not take internally.

Avoid breathing vapor or mist.

Do not use in tank or pit without proper protection.

Read Material Safety Data Sheet before use of this product.

***Fast. Reliable. Accurate. Superior Coatings of America***

Address: P.O. Box 409 Clinton, MI 49236    Office Phone: 734-580-2089    Email: [sales@superiorsalesdist.com](mailto:sales@superiorsalesdist.com)  
[www.superiorsalesdist.com](http://www.superiorsalesdist.com)