



Technical Data Sheet

TT-P-1757B TY. I, CL.N
NON-CHROMATE PRIMER
PAGE 1 OF 2

PRODUCT: A one-component, alkyd base, corrosion-inhibiting nonchromate primer.

DESCRIPTION: TT-P-1757B Ty.I, Cl.N Primer is a single component, non-chromate pigmented, low-moisture sensitivity primer primarily intended for spray application on surface treated aluminum or surface treated with pre-treatment coatings MIL-C-8514C or DOD-P-15328D. This primer may be used with or without top coating. When suitable thinned, this primer may be used for dip or flowcoat application.

PROPERTIES:

SOLIDS(Weight)..... 59% Minimum
FINENESS OF GRIND..... 6 Minimum
COLORS..... Green & Yellow

DRYING TIME:

DRY HARD..... Within 15 Minutes
THINNER..... MIL-T-81772B TY.III
SHELF LIFE..... 1 Year

SURFACE PREPARATION: *Steel, Non-Ferrous Metals & Galvanizing.*

Surface to be coated must be clean, dry, and free of all foreign contaminants including grease, oil, dirt and paint. Clean in accordance with SSPC-SP-1. Most metals should be sanded, except aluminum, which must have a base coat of pre-treatment wash primer MIL-C-8514C, followed by one wet coat of TT-P-1757B Ty.I, Cl.N. Alloys that oxidize must be lightly sanded to remove all loose material. Dirt and dust are best removed with a stiff bristle brush and by compressed air. For exterior use and nonferrous metals, it is recommended that TT-P-1757B Ty. I, Cl.N be applied over pre-treatment coating conforming to MIL-C-8514C or DOD-P-15328D. Grease and oil should be removed by cleaning with appropriate solvents such as mineral spirits, lacquer wash thinner or xylene.

Fast. Reliable. Accurate. Superior Coatings of America

Address: P.O. Box 409 Clinton, MI 49236 Office Phone: 734-580-2089 Email: sales@superiorsalesdist.com
www.superiorsalesdist.com



Technical Data Sheet

TT-P-1757B TY. I,
CL.N
NON-CHROMATE PRIMER
PAGE 2 OF 2

MIXING/APPLICATION INSTRUCTIONS: Apply by spray, brush, or dip to deposit a hiding coat of primer. A wet coat is necessary to secure maximum adhesion and corrosion inhibiting properties. For spraying, thin up to 15% by volume or as needed with thinner per TT-X-916 or MIL-T-81772B TY.III.

ADVANTAGES:

1. Corrosion Inhibiting
2. Use with or without Topcoat
3. Non-Chromate Rust Inhibitor
4. Low-Moisture Sensitivity
5. Meets Government Specifications

PRECAUTIONS:

KEEP OUT OF REACH OF CHILDREN.
USE WITH ADEQUATE VENTILATION.
AVOID CONTACT WITH SKIN AND EYES.
READ MATERIAL SAFETY DATA SHEET BEFORE USING.
CONTENTS ARE FLAMMABLE.

Fast. Reliable. Accurate. Superior Coatings of America

Address: P.O. Box 409 Clinton, MI 49236 Office Phone: 734-580-2089 Email: sales@superiorsalesdist.com
www.superiorsalesdist.com