



TT-P-645C Alkyd Based Primer

Technical Data Sheet (Page 1 of 2)

Description:

TT-P-645C Primer is a single component primer, primarily intended for use as a general primer for steel and properly prepared aluminum.

Physical Properties:

Solids (Weight):	78.8% Minimum
Solids (Volume):	56% Minimum
Weight / Gallon:	13.3 – 13.7 Lbs
Colors:	Green
Thinner:	MIL-T-81772B Type III
Shelf Life:	1 Year
Drying Time:	
To Touch:	Within 6 Hours
To Recoat:	6-8 Hours
To Cure:	14 Days

Application Characteristics:

- (1) Corrosion Inhibiting
- (2) High Solids, Low VOC
- (3) Fast Dry
- (4) Use on ferrous and non-ferrous metals
- (5) Meets Government Specification TT-P-645C

Fast. Reliable. Accurate. Superior Coatings of America

Address: P.O. Box 409 Clinton, MI 49236

Email: sales@superiorsalesdist.com

www.superiorsalesdist.com



TT-P-645C Alkyd Based Primer

Technical Data Sheet (Page 2 of 2)

SURFACE PREPARATION: Surface to be coated must be clean, dry, and free of all foreign contaminants including grease, oil, dirt and paint. Clean in accordance with SSPC-SP-1. Most metals should be sanded, except aluminum, which must have a base coat of pre-treatment wash primer MIL-C-8514C, followed by one wet coat of TT-P-645C. Alloys that oxidize must be lightly sanded to remove all loose material. Dirt and dust are best removed with a stiff bristle brush and by compressed air. For exterior use and non-ferrous metals, it is recommended that TT-P-645C be applied over pre-treatment coating conforming to MIL-C-8514C or DOD-P-15328D. Grease and oil should be removed by cleaning with appropriate solvents such as mineral spirits, lacquer wash thinner or xylene.

APPLICATION & REDUCTION: Apply by spray, or brush/roll small areas to deposit a hiding coat of primer. A wet coat is necessary to secure maximum adhesion and corrosion inhibiting properties. For application by spray, thin sparingly with Xylene per TT-X-916 or MIL-T-81772B TY. III only as need for proper atomization. For brush or roller, use at packaged viscosity.

PRECAUTIONS:

KEEP OUT OF REACH OF CHILDREN.

USE WITH ADEQUATE VENTILATION.

AVOID CONTACT WITH SKIN AND EYES.

READ MATERIAL SAFETY DATA SHEET BEFORE USING

KEEP FROM FREEZING

Fast. Reliable. Accurate. Superior Coatings of America

Address: P.O. Box 409 Clinton, MI 49236

Email: sales@superiorsalesdist.com

www.superiorsalesdist.com